



SAMSARA RUBBER RECLAIMERS LLP



TECHNICAL DATASHEET

HI-TENSILE RECLAIM RUBBER

GRADE SAMSARA - HT10

PROPERTIES	UNITS	TEST METHOD	SAMSARA - HT10
PHYSICAL PROPERTIES			
MOONEY VISCOSITY	ML (1+4)@100C	ASTM D1646 / IS 6306	50 - 60
HARDNESS	Shore A	ASTM D2240 / IS 6306	55 - 65
TENSILE STRENGTH	kg/cm ²	ASTM D412 / IS 6306	100 Min.
ELONGATION AT BREAK	%	ASTM D412 / IS 6306	350 Min.
SPECIFIC GRAVITY	gm/cc	ASTM D297 / IS 6306	1.14 ± 0.03
CHEMICAL PROPERTIES			
CARBON BLACK	%	ASTM E1131 / IS 6306	18 - 27
ASH CONTENT	%	ASTM D297 / IS 6306	9 Max.
ACETONE EXTRACT	%	ASTM D297 / IS 6306	14 ± 3
VOLATILE MATTER	%	-	1 Max.
RUBBER HYDROCARBON	%	ASTM E1131 / IS 6306	47 Min.

710, 7th Floor, Emaar Mgf Capital Tower, 1, Mehrauli-Gurgaon Rd, Sikanderpur, Sector 26, Gurugram, Haryana 122002

Plot No. A-62, Taloja Industrial Area of MIDC, Taloja City, Taloja Panchnad CT)-410208, Taluka Panvel, Distt. Raigad, Navi Mumbai (Maharashtra)

info@samsararubber.in



+91 9910077631



www.samsararubber.in